

TABLE 1. RESULTS OF CRACK RESISTANCE TESTING

Samples	Maximum Crack Width (mm)	Average Crack Area Per Crack (mm²)
0% silane (reference)	4.55	139
1% silane	2.13	27
3% silane	1.64	22
5% silane	1.13	18